

XADO THERMOLUBE 300

TECHNICAL INFORMATION

Meets the requirements:

NLGI 2 (ASMT D D217)

KF FK 2 U-30 (DIN 51 502)

Technical data:

Appearance	soft white grease
Drop point, °C, not lower than:	250
Penetration at 25°C, mm ⁻¹	265-295
Temperature range, °C	
long-term:	-30...+250
short-term:	до +280
Lubricating properties during the test on a four-ball machine (20±5) °C:	
Weld point, N	≥ 4900
Corrosive impact on metal	Withstands

Application instructions:

- It is recommended to conduct a compatibility test for the grease and contacting materials before commercial application;
- Clean the contacting surfaces before applying the grease;;
- It is not recommended to mix the grease with other lubricating materials;
- The grease can be applied manually, using a brush, or using a manual lubricating gun;
- By manual application: remove the old grease and pack not more than 2/3 of the free volume of the bearing (assembly) with the grease;
- When using a lubricating gun: introduce the grease through the lubricator until it shows in clearances of the lubricated joint.

Packaging:

syringe 30 ml Art. XA 30128

tube 125 ml Art. XA 30228

can 1 kg Art. XA 30528